

JAC SHEETS

JAC DATA LASER FSC® CERTIFIED

Print carrier

JAC® Data Laser FSC® Certified is a white laser paper (TCF) for monochrome laser printers and copiers. The face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

In copying and laser printing, this paper excels by a perfect toner key, a clean print image and a high ink resolution. With Inkjet printing, good printing results are obtained in the printer's normal paper mode

Printing technologies:

Copier, laser printing and limited use for inkjet and offset printing

For technical guidance please visit our website under.

Average values

	Data Laser FSC® Certified
Weight (g/m ²)	68
Thickness (micron)	78
Tensile strength longitudinal (kN/m)	5.2
Opacity (%)	89
Shelf life of laminate (years) ¹	2

¹ Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%

For information regarding EHS regulation please visit our website under downloads "Guidelines for Use "5.12 Product Compliance JAC® Offset".

Adhesive

DURO D 2000 is a dispersion-based permanent acrylic adhesive displaying very good processing properties and excellent guillotining behaviour. Its good adhesion permits use on a diversity of surfaces, such as paper, steel, glass etc. It also displays very good UV stability.

Average values

	D200
Adhesion (N/25 mm) (FTM2 on st. steel/20 min. bond time)	9.2
Tack (N/25 mm) (FTM9 on glass)	9.6
Recommended minimum application temperature (°C)	>+5
Heat resistance up to 24 hrs (°C)	+80
up to 1 hr (°C)	+110
Resistance to cold (°C) ² down to	- 40

² Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

Silicone paper

B 85 – siliconized kraft, wood-free, special-purpose paper, moisture-stabilized through a special coating on one side. It displays high dimensional stability and excellent flatness. This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

Average values

	B 85
Weight (g/m ²)	78
Thickness	82

Issue May 2021

Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>

JAC® is registered trademark of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.