

## Print carrier

## Average values

This paper range is especially dedicated for applications, where a special finish is requested like high and premium goods, such as wine, spirits and packaging of specialist foods. All print carriers have a wet-strength and fungicidal treatment. Following versions are available:

- **Matt Design:** white, matt coated, supercalendered
- **Hammered White:** white, uncoated, matt with "hammered" tactile embossed finish
- **Rustic White:** white, uncoated matt with felt marked finish
- **Verge Creme:** cream, uncoated, matt, laid watermarked with a tactile "handmade" appearance and feel
- **Verge Blanc:** white, uncoated, matt, laid watermarked with a tactile "handmade" appearance and feel
- **Natural Wood:** natural, unbleached, uncoated, laid watermarked

### Printing processes:

All classical printing processes (flexographic, offset, screen). This series is also printable with Dry Toner printers.

|  | Matt Design | Hammered White | Rustic White | Verge Creme | Verge Blanc | Verge Wood |
|--|-------------|----------------|--------------|-------------|-------------|------------|
| Weight (g/m <sup>2</sup> )                   | 90          | 90             | 90           | 80          | 80          | 90         |
| Thickness (µm)                               | 86          | 118            | 130          | 120         | 120         | 88         |
| Shelf life of laminate <sup>1)</sup> (years) | 2           | 2              | 2            | 2           | 2           | 2          |

<sup>1)</sup> Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%.

For information regarding EHS regulation, please visit our website under downloads "Guidelines for Use 5.12 Product Compliance JAC Offset".

For technical guidance please visit our website under please visit our website under downloads "Guidelines for Use" - Offset printing.

## Adhesive

## Average values

**Duro D2010** features high initial tack, excellent adhesion and good low temperature performance on a wide variety of substrates

|   | DURO      |
|---|-----------|
| Adhesion (N/25 mm)<br>(FTM2 on st. steel/20 min. bond time) | 7         |
| Tack (N/25 mm)<br>(FTM9 on glass)                           | 17        |
| Recommended minimum application temperature (°C)            | >+5       |
| Service temperature range (°C)                              | -20 to 80 |

<sup>2)</sup> Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

## Silicone paper

## Average values

**B80** is a siliconized, special-purpose, bleached kraft paper. It is moisture-stabilized through a special coating on one side and display high dimensional stability and excellent flatness.

|                            | B 80 |
|----------------------------|------|
| Weight (g/m <sup>2</sup> ) | 80   |
| Thickness                  | 79   |

Issue May 2021

### Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>

JAC\* is registered trademark of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.