

JAC SHEETS

JAC ECOPLUS PAPERPRINT

Print carrier

Average values

JAC® ECOPLUS PAPER-PRINT is an environmentally friendly, white, matt polyolefin film which has been specially developed for offset printing with conventional inks.

Offset-printed: with both purely oxidative drying and UV-curing inks.

Screen printed: with conventional (i.e solvent-based) and UV-curing inks.

JAC® ECOPLUS PAPER-PRINT is special weather-resistant and extremely absorbent surface coating.

For print and application guidance please visit our web side under "Application of JAC films" and "Printing of JAC® films in Offset".

JAC® ECOPLUS PAPER-PRINT not only permits fast ink drying but also displays good flatness and hence excellent smoothness of passage through the printing machine. Consult your ink supplier about suitable printing inks for your particular application.

	28080
Weight (g/m ²)	75
Thickness (micron)	95
Tensile strength	
longitudinal (N/15mm)	45
Transverse (N/15mm)	35
Opacity (%)	92
Shelf life of laminate (years) ¹⁾	2

¹⁾ Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%.

For information regarding EHS regulation please visit our website under downloads "Guidelines for Use "5.12 Product Compliance JAC® Offset.

Adhesive

Average values

PERMANENT is a water-based permanent acrylic adhesive that has been specially developed for polyolefin films.

Note: Permanent is recommended only for dry application.

	PERMANENT
Adhesion (N/25 mm) (FTM 1 on st. steel/20 min)	15.4
Tack (N) (FTM 9 on st. steel)	10.3
Recommended minimum application temperature (°C)	+5
Heat resistance (in °C)	+80
Resistance to cold (°C) ²⁾ down to	- 20

²⁾ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs
Heat resistance refers only to adhesive applied on steel.
Quality of front material can be affected when exposed to higher temperatures.

Silicone paper

Average values

B 145 is a siliconized, special-purpose lightweight board, wood-free, matt on reverse side, moisture-stabilized through specially impregnated fibres and special coating, hence its excellent flatness.

	B 145
Weight (g/m ²)	130
Thickness (µm)	140

Issue July 2024

Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>

JAC® is registered trademark of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.