

JAC SHEETS

JAC OPAQUE FSC® CERTIFIED

Print carrier

Average values

JAC® OPAQUE is a range of opaque self-adhesive papers for re-labelling applications where the existing texts must be completely concealed, e.g., for text or price corrections. These self-adhesive papers display excellent opacity. It is a series of specially coated matt, semi-gloss and gloss papers.

JAC® SCRIPT OPAQUE FSC® Certified A calendared, white writing paper displaying very good printing properties. The face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

JAC® CHROMO GLOSS OPAQUE FSC® Certified A specially coated, white, gloss paper which is particularly suitable for multi-colour labels. The face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

JAC® CHROMO MATT OPAQUE FSC® Certified A specially coated, white, matt paper which is particularly suitable for the multi-colour offset printing of high-quality labels. The face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

For technical guidance please visit our website under downloads "Guidelines for use – Offset printing."

| | Script Opaque FSC® Certified | Chromo Gloss Opaque FSC® Certified | Chromo Matt Opaque FSC® Certified |
|---|------------------------------------|--|---|
| Weight (g/m²) | 86 | 102 | 103 |
| Thickness (µm) | 85 | 100 | 100 |
| Opacity (%) | | 98 | |
| Shelf life of laminate ¹⁾ (years) | 2 | 2 | 2 |

¹⁾ Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%.

For information regarding EHS regulation, please visit our website under downloads "Guidelines for Use 5.12 Product Compliance JAC Offset".

Adhesive

Average values

PERMANENT is a water-based permanent acrylic adhesive displaying very good processing properties and excellent guillotining behaviour. Its good adhesion permits use on a diversity of surfaces, such as paper, steel, glass etc. It also displays very good UV stability.

| | PERMANENT |
|---|-----------|
| Adhesion (N/25 mm) (FTM 1 on st. steel/20 min. bond time) | 15.4 |
| Tack (N) (FTM 9 on st. steel) | 10.3 |
| Recommended minimum application temperature (°C) | +5 |
| Heat resistance (in °C) | +80 |
| Resistance to cold (°C) ²⁾ down to | - 20 |

²⁾ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

Silicone paper

Average values

B 85 – a siliconized, wood-free, special-purpose paper. It is moisture-stabilized through a special coating on one side. B85 displays high dimensional stability and excellent flatness. This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

B 110 – a siliconized, wood-free, special-purpose paper. It is moisture-stabilized and displays very high dimensional stability and excellent flatness. This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

| | B 85 | B 110 |
|----------------|------|-------|
| Weight (g/m²) | 80 | 90 |
| Thickness (µm) | 81 | 90 |

Issue July 2024

Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>

JAC® is registered trademark of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.