

# JAC SHEETS

## JAC SERILUX PLUS

### Print carrier

### Average values

**JAC® SERILUX PLUS** is a flexible PVC film for UV- and conventional offset printing. The film is used for the production of high-quality labels for indoor and outdoor application.

**JAC® SERILUX PLUS** displays a high degree of tear resistance and tear propagation resistance. They also display relatively good ageing stability, water resistance and lightfastness, depending on the actual applications for which they are used. For technical guidance please see our web side under "5.5 Application of JAC® films"

**JAC® SERILUX PLUS** as mentioned is suitable for conventional offset printing but with purely oxidative drying inks which are resistant to plasticiser and suitable for films. Consult your printing ink supplier about suitable printing inks for your particular application. For more details regarding Offset printing on films please see our website "5.6 Printing of JAC® films in Offset". For printing with translucent inks please also see our technical documentation on our website.

The following print carriers are available ex. stock:

JAC® SERILUX 70090 – crystal clear, gloss

JAC® SERILUX 72090 – white, gloss approx. RAL 9016.

Type N°	70090	72090
Weight (g/m <sup>2</sup> )	104	122
Thickness (µm)	90	90
Tensile strength longitudinal (kN/m)	23	29
Wearing conditions <sup>1)</sup> (years)	2	2

<sup>1)</sup> Under normal climatic conditions as prevailing in Central Europe.

For information regarding EHS regulation, please visit our website under downloads "Guidelines for Use 5.12 Product Compliance JAC Offset".

### Adhesive

### Average values

**PERMANENT** is a water-based permanent acrylic adhesive. It has been specially developed for flexible PVC films. **PERMANENT** is distinguished by its high transparency and UV stability.

	PERMANENT
Adhesion (N/25 mm) (FTM 1 on st. steel/20 min. bond time)	15.4
Tack (N) (FTM 9 on stainless steel)	10.3
Recommended minimum application temperature (°C)	+5
Heat resistance (in °C)	+80
Resistance to cold (°C) <sup>3)</sup>	- 20
Ageing stability <sup>4)</sup>	good
Shelf life of laminate (years) <sup>5)</sup>	1

<sup>2)</sup> Strength of adhesion may be adversely affected by a possible migration of plasticizer from the flexible PVC film into the adhesive.

<sup>3)</sup> Not fully resistant until after adhesion reaches full strength - after at least 24 hrs

<sup>4)</sup> If not exposed to direct sunlight; applied at room temperature

<sup>5)</sup> Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%.

### Silicone paper

### Average values

**B120** is a siliconized, special-purpose lightweight board, wood-free, matt on reverse side, moisture-stabilized through specially impregnated fibres and special coating, hence its excellent flatness.

	B 120
Weight (g/m <sup>2</sup> )	120
Thickness (µm)	118

**B120 SPLIT** is as above, but with scored lines running in machine direction and spaced 6,25 cm apart serving as a peel-off aid.

Issue July 2024

#### Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>

JAC® is registered trademark of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.