

JAC SHEETS

JAC COLOURS FSC® CERTIFIED

Print carrier

Average values

JAC® coated coloured papers

JAC® Yellow FSC® Certified - the face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

JAC® Green FSC® Certified - the face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

JAC® Blue FSC® Certified - the face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

JAC® Red FSC® Certified - the face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

Printing processes: All classical printing processes (flexographic, letterpress, offset).

	JAC Yellow FSC® Certified	JAC Green FSC® Certified	JAC Blue FSC® Certified	JAC Red FSC® Certified
Weight (g/m ²)	80	80	80	80
Thickness (µm)	82	82	82	82
Shelf life of laminate ¹⁾ (years)	2	2	2	2

¹⁾ Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%.

For information regarding EHS regulation, please visit our website under downloads "Guidelines for Use 5.12 Product Compliance JAC Offset".

For technical guidance please visit our website under please visit our website under downloads "Guidelines for Use" - Offset printing.

Adhesive

Average values

PERMANENT is a general purpose permanent adhesive for most common substrates.

PERMANENT

Adhesion (N/25 mm) (FTM 1 on st. steel/20 min. bond time)	15.4
Tack (N) (FTM 9 on st. steel)	10.3
Recommended minimum application temperature (°C)	+5
Heat resistance (in °C)	+80
Resistance to cold (°C) ¹⁾ down to	- 20

¹⁾ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

Silicone paper

Average values

B 85 – siliconized, wood-free, special-purpose paper. They are moisture-stabilized through a special coating on one side and display high dimensional stability and excellent flatness. This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

B 110 – standard backing for Split constructions. This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

	B 85	B 110
Weight (g/m ²)	80	90
Thickness (µm)	81	90

Issue July 2024

Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>

JAC® is registered trademark of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.