

JAC SHEETS

JAC SCRIPT/SCRIPT FSC® CERTIFIED

SCRIPT 115 FSC® CERTIFIED

Print carrier

Average values

JAC® Script White writing papers

JAC® Script FSC® Certified The white, supercalendered paper face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

JAC® Script 115 FSC® Certified - the white, supercalendered writing paper face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

Printing processes: All classical printing processes (flexographic, letterpress, offset).

	Script FSC® Certified	Script 115 FSC® Certified
Weight (g/m ²)	80	120
Thickness (µm)	76	106
Shelf life of laminate ¹⁾ (years)	2	2

¹⁾ Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%.

For information regarding EHS regulation, please visit our website under downloads "Guidelines for Use 5.12 Product Compliance JAC Offset".

For technical guidance please visit our website under please visit our website under downloads "Guidelines for Use" - Offset printing.

Adhesive

Average values

All 3 adhesives are acrylic water-based, displaying very good application and processing properties including good to excellent guillotining behaviour and very good UV stability.

PERMANENT is a general purpose permanent adhesive for most common substrates.

EXTRAPERMANENT where PERMANENT is not sufficient like on rough and plastic substrates.

REMOVABLE is a general purpose removable adhesive. It displays good adhesion on-and residue-free removal from-most smooth, dry surfaces such as glass, metal, polyolefins. Note: For other types of surface, trials under actual application conditions are recommended in order to ascertain suitability.

	PERMANENT	EXTRA- PERMANENT	REMOVABLE
Adhesion (N/25 mm) (FTM 2 on st. steel/20 min. bond time)	9.2	11	2.6
Tack (N) (FTM 9 on glass)	9.6	15.4	3.5
Recommended minimum application temperature (°C)	>+5	>+5	>+5
Heat resistance up to 24 hrs (°C)	+80	+80	+80
up to 1 hr (°C)	+110	+110	+110
Resistance to cold (°C) ¹⁾ down to	- 40	- 40	- 40

¹⁾ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

Silicone paper

Average values

B 85 / B110 – siliconized, wood-free, special-purpose paper. They are moisture-stabilized through a special coating on one side and display high dimensional stability and excellent flatness. This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

	B 85	B 110
Weight (g/m ²)	80	86
Thickness (µm)	81	87

B 110 – standard backing for Split constructions. This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

Issue December 2023

Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>

JAC® is registered trademark of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.