

# JAC SHEETS

## JAC TAG FSC® CERTIFIED

### Print carrier

### Average values

**JAC® TAG FSC® Certified** is white, wood-free, supercalendered board. It enjoys application wherever a face material of particularly high stability is required. The face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

For technical guidance please visit our website under Downloads "Guidelines for use – Offset printing.

	<b>TAG FSC® Certified</b>
Weight (g/m <sup>2</sup> )	170
Thickness (micron)	150
Surface smoothness (PPS)	2.8 µm
Opacity (%)	98
Shelf life of laminate (years) <sup>1)</sup>	2

<sup>1</sup> Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%

For technical guidance please visit our website under please visit our website under downloads "Guidelines for Use " - Offset printing.

### Adhesive

### Average values

**EXTRAPERMANENT** is an acrylic water-based adhesive, displaying very good application and processing properties including good to excellent guillotining behaviour and very good UV stability.

It shows good performance on rough and plastic substrates.

	<b>EXTRAPERMANENT</b>
Adhesion (N/25 mm) (FTM 1 on st. steel/20 min. bond time)	17.2
Tack (N) (FTM 9 on st. steel.)	11
Recommended minimum application temperature (°C)	+5
Heat resistance (in °C)	+80
Resistance to cold (°C) <sup>2)</sup> down to	- 20

<sup>1</sup> Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

### Silicone paper

### Average values

**B 110** – a siliconized, wood-free, special-purpose paper. It is moisture-stabilized and displays very high dimensional stability and excellent flatness. This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

	<b>B 110</b>
Weight (g/m <sup>2</sup> )	86
Thickness (µm)	87

Issue December 2023

#### Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>

JAC® is registered trademark of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.